



EXPERIENCE TO PERFORM

TECHNICAL DATA SHEET

MOTORBLACK SILICONE SEAL

- *PRODUCT DESCRIPTION*

Motorblack is a single component silicone elastomer with acetic cross-linking system.

Its technical properties are superior to normal silicones, allowing the product to be used in the automotive industry where resistance capacities are required under particularly severe conditions of temperature, pressure and resistance to solvents, lubricating fluids and mechanical stresses.

Silicone has excellent dielectric properties and excellent adhesion to most materials.

The product is specifically designed for sealing oil sumps of "Fire" engines and it is recommended in the industrial sector as a sealant for the moving parts of machines, such as, for example, pumps, turbines, compressors and as an alternative to pre-formed sealants. In the electrical sector, it is used as an insulator. It is suitable for bonding already polymerized silicone and wherever seals resistant to high temperatures, oils and solvents are required.

- *TECHNICAL SPECIFICATIONS*

- Cross-linking type acetic
- Physical appearance Thixo paste
- Temperature of application $+5 \div +40^{\circ}\text{C}$
- Operating temperature $-70 \div +250^{\circ}\text{C}$
for short periods $+ 300^{\circ}\text{C}$
- Specific weight 1.04 g/ml
- Skin formation 6 minutes
- Polymerization velocity 4 mm/day
- Modulus of elasticity 0.6 MPa
- Tensile strength 2 MPa
- Elongation at break 425%
- Dielectric strength 20 KV/mm
- Shore A hardness 24
- Heat conductivity at $+30^{\circ}\text{C}$ 0.2 W/mK
at $+150^{\circ}\text{C}$ 0.16 W/mK

After cross-linking, the product is resistant to water, fuels, mineral and synthetic oils, radiator liquids.

- *METHOD OF USE*

Use on clean and grease-free surfaces. Assemble the pieces after around 20 minutes (skin formation)

It is possible to accelerate the cross-linking through heat.

- *STORAGE*

Product validity after packaging in sealed package and stored at room temperature: minimum 24 months

- *NOTES*

During hardening, traces of acetic acid vapors are released. Avoid extended contact of the product with the skin and the eyes; in the event of contact with eyes, wash abundantly with water.

- *PACKAGING*

Aluminum tube

Contents 60 g

Code 0094

- *NOTES*

For information on product safety, please consult the safety sheet.

R&D 01.02.2008

The data contained herein are the result of technological research by our laboratories and are given for informative purposes only. We exclude any liability deriving from the incorrect choice or application of the product and from the lack of the necessary precautions, which should be carefully checked by the user. For information, please contact our Technical Dept. on no. +39 02924361

AREXONS S.p.A. A SOCIO UNICO
Via Antica di Cassano, 23
20063 Cernusco sul Naviglio (MI) Italy
Capitale Sociale: € 15.000.000,00 I.V.
Registro delle Imprese di Milano n. 09728360968
Codice Fiscale e Partita IVA 09728360968
Direzione e coordinamento ex art. 2497 c.c. PLI (Netherlands) B.V.
Centralino 02 92436.1
Fax 02 92436.306
www.arexons.com

A wholly-owned subsidiary of PETRONAS

Sistemi di gestione di qualità della società Arexons S.p.A.
certificati ISO 9001 da LRQA.

Sistemi di gestione di ambiente e sicurezza della società Arexons S.p.A.
certificati ISO 14001 e OHSAS 18001 da Bureau Veritas.

